

ATLAS WELDING BLANKET

Crepin

CREPIM Société par Actions Simplifiée -792 178 816 R.C.S. ARRAS Siege social : Parc de la Porte Nord - rue Christophe Colomb. 62700 BRUAY LA BUISSIERE France Tél.: 03.21.61.64.00 Fax:: 03.21.61.64.01 E-mail : <u>contast@cegimf</u>; www.crepim.fr SIRET 792 178 816 00015 / APE 7112B / T.V.A. FR85 792 178 816

E09.09 - Révision D du 03/09/2014

Dossier/File 1303/10/351 G - Page 5 / 6

Le classement supplémentaire en relation avec les gouttelettes/particules enflammées est // Complementary classification in relation to fall of flaming droplets/particles is: **d0**.

Le format du classement de réaction au feu pour les produits de construction, à l'exception des revêtements de sol et des produits d'isolation thermique pour conduites linéaires est / The format of the reaction to fire classification for construction products excluding flooring and linear pipe thermal insulation products is:

Comportement au feu Fire behaviour		Production de fumée Smoke production			Gouttelettes enflammées Flaming droplets	
A2	-	S	1	,	d	0

C'est-à-dire / Namely, A2 - s1, d0

Classement de réaction au feu /	12 1 10
Reaction to fire classification :	A2-s1,d0

4.3 Domaine d'application / Field of application

Le présent classement est valable pour les paramètres suivants liés au produit / The classification is valid for the following product parameters :

Composition / Composition:	Toile de verre de 430 à $660g/m^2$ et enduction de 30 à $60g/m^2$ de polyuréthane réparti sur une ou deux faces / 430 to 660gr glass and 30 to 60 gr of Polyurethane distributed on one or two sides.
Epaisseur / Thickness:	de 0,41 à 0,7mm / Between 0,41 and 0,7mm
Masse volumique / Density :	de 1014 à 1146 kg/m ³ / Between 1014 and 1146kg/m ³
	• • • • • • • • • • • • • • • • • • •

Masse surfacique / Surface mass: de 460 à 720 g/m² / Between 460 and 720g/m²

Le classement est valable pour les conditions d'utilisation finale suivantes / The classification is valid for the following end-use condition:

Fixé mécaniquement et suspendu librement par-dessus un cadre métallique A1 et densité 2700kg/m3 (représentatif de tous les supports métalliques de qualité A1 ayant une masse volumique supérieure à 2025kg/m3 et dont le point de fusion est supérieur ou égal à 500°C) / Mechanically fixed and freely suspended over a metal frame A1 density 2700kg/m3 (representative of every A1 metallic substrate having a density superior to 2025kg/m3 and having a fusion point superior or equal to 500°C. Avec une lame d'air de 40mm ou moins / With an air gap 40mm thick or less.

> Ce rapport de classement comprend 6 pages et ne peut être utilisé ou reproduit que dans son intégralité This Classification Report consists of 6 pages and may only be used or reproduced in its entirety

Commercial 1/1

Certification 1/1

Safety 1/5

Technical Specifications 1/1



INFOSHEET

ATLAS WELDING BLANKET

1. IDENTIFICATION OF THE SUBSTANCE / PREPARATION AND COMPANY **Product description** Glass fibre material Manufacturer / Supplier Cepro International BV Date of issue February 2014 P.O. Box 183 5120 AD Rijen The Netherlands Tel. no. for information / emergency +31 (0)161 22 64 72 Fax no. for information / emergency +31 (0)161 22 49 73 2. HAZARD INFORMATION Classification of the substance or mixture Classification according to Regulation (EC) No 1272/2008 [CLP] Not determined Classification according to Regulation 67/548/EEC or 1999/45/EC No classification Label elements The product does not require a hazard warning label in accordance with EC-directives. This product is an article and therefore it does not require labelling according to EC directives/GefStoffV. Other hazards **Physico-chemical hazards** no particular hazards known. **Environmental hazards** no particular hazards known. Other hazards none 3. COMPOSITION / INFORMATION ON INGREDIENTS Range [%] Substance glass 85-100 CAS:65997-17-3, EINECS/ELINCS: 266-046-0 Comment on component parts No dangerous components. Substances of Very High Concern - SVHC: substances are not contained or are below 0,1 %. 4. FIRST AID MEASURES **Description of first aid measures** General information Change soaked clothing. Inhalation Ensure supply of fresh air. In the event of symptoms refer for medical treatment. Skin contact When in contact with the skin, clean with soap and water. Consult a doctor if skin irritation persists. In case of contact with eyes rinse thoroughly with plenty of water and seek medical Eve contact advice. Ingestion Not applicable

Most important symptoms and effects, both acute and delayed No information available

Indication of any immediate medical attention and special treatment needed Treat symptomatically Forward this sheet to the doctor.





INFOSHEET

WELDING BLANKET AS ΔΤΙ

5. FIRE-FIGHTING ME	AJUREJ
Suitable extinguishing media	Product itself is non-combustible. Fire extinguishing method of surrounding areas must be considered.
Extinguishing media that must not be used	None.
Special hazards arising from	the substance or mixture Unknown risk of formation of toxic pyrolysis products.
Advice for fire-fighters	not applicable Fire residues and contaminated fire-fighting water must be disposed of in accordance with the local regulations.
6. ACCIDENTAL RELE	
	ive equipment and emergency procedures
Environmental precautions Methods and material for cont	Avoid dust formation. Use breathing apparatus if exposed to dust. Not applicable
Environmental precautions Methods and material for cont	Avoid dust formation. Use breathing apparatus if exposed to dust. Not applicable ainment cleaning up Dispose of absorbed material in accordance with the regulations. Take up mechanically. See section 8+13
Environmental precautions Methods and material for cont Reference to other sections 7. HANDLING AND ST Precautions for safe handling	Avoid dust formation. Use breathing apparatus if exposed to dust. Not applicable ainment cleaning up Dispose of absorbed material in accordance with the regulations. Take up mechanically. See section 8+13
Environmental precautions Methods and material for cont Reference to other sections 7. HANDLING AND ST Precautions for safe handling	Avoid dust formation. Use breathing apparatus if exposed to dust. Not applicable ainment cleaning up Dispose of absorbed material in accordance with the regulations. Take up mechanically. See section 8+13 ORAGE With mechanical processing however fibers can be set free. Avoid the formation and depositions of dust. Provide vacuuming if dust raised. Dust deposits that cannot be avoided must be taken up regularly. Wash hands before breaks and after work. Use barrier skin cream take off contaminated clothing and wash before reuse.

ntrol paramotors

Control parameters	
Ingredients with occupation	nal exposure limits to be monitored (GB)
Range [%]	Substance
85-100	glass
	ČAS: 65997-17-3, EINECS/ELINCS: 266-046-0
	Long-term exposure: TLV-TWA: 1 f/cc (respirable): 5 mg/m³ (inhalable (ACGHIH
Exposure controls	
Additional advice on system	n design
-	Ensure adequate ventilation on workstation
	To pay attention to dust limit value (ACGHI-2011: 10 mg/m ³ particle inhalable;
	3 mg/m ³ particle respirable).
Eye protection	Safety glasses
Hand protection	The details concerned are recommendations. Please contact the glove supplier
•	for further information.
	Leather (EN 388).
Skin protection	Long-sleeved work clothes.
	•

```
Safety 2/5
```



DING BLANKET **H**

Other	Avoid contact with eyes and skin.
	Do not inhale dust.
	Personal protective equipment should be selected specifically for the working
	place, depending on concentration and quantity of the hazardous substances
	handled. The resistance of these equipments to chemicals should be
	ascertained with the respective supplier.
Respiratory protection:	Breathing apparatus in the event of high concentrations.
	Short term: filter apparatus, filter P2.
Thermal hazards	No information available
Delimitation and monitorin	g of the environmental exposition:
	not determined
	not determined
9 PHYSICAL AND	
STITIOICAL AND	

FOSHEE

Form	Solid in different forms.	Vapour pressure (kPa)	Not applicable.
Colour	Various.	Density (g/m)	Not determinated.
Odour	Odourless.	Bulk density (kg/m³)	Not applicable.
pH-value	Not applicable.	Solubility in water	Immiscible.
pH-value, 1 %	Not applicable.	Partition coefficient: n-octanol / water	Not applicable.
Boiling point (°C)	Not applicable.	Viscosity	Not applicable.
Flash point (°C)	Not applicable.	Relative vapour density determined in air	Not applicable.
Flammability (°C)	Not applicable.	Evaporation speed	Not applicable.
Lower explosion limit	Not applicable.	Melting point (°C)	Not determinated.
Upper explosion limit	Not applicable.	Autoignition temp. (°C)	Not applicable.
Combustible properties	No.	Decomposition temp. (°C)	Not applicable.

Other information

Conditions to avoid Incompatible materials

Reactivity

No information available

10. STABILITY AND REACTIVITY

No hazardous reactions known Stable under normal ambient conditions (ambient temperature)

Chemical stability Possibility of hazardous reactions

No hazardous reactions known No information available No information available Hazardous decompostions products

11. TOXICOLOGICAL INFORMATION

Acute oral toxicity: not determined Acute dermal toxicity: not determined Acute inhalational toxicity: not determined Irritant effect on eye: not determined Irritant effect on skin: not determined Sensitization: not determined not determined Subacute toxicity: Chronic toxicity: not determined Mutagenicity: not determined **Reproduction toxicity:** not determined Carcinogenicity: not determined Experiences made in practice: Contains fibres with diameter > 6 micrometers. The filament is not breathable (WHO). Fiber abrasion can cause mechanical skin irritation. **General remarks:** No classification on the basis of the calculation procedure of the preparation directive.

> Technical Specifications 1/1

Version 003 - Check our website for the latest version

Commercial 1/1

Certification 1/1

Safety 3/5



ATLAS WELDING BLANKET

12. ECOLOGICAL INFORMATION

Toxicity

Persistence and degradability Behaviour in environment co Behaviour in sewage plant Biological degradability	
Bioaccumulative potential Mobility in soil	No information available
Results of PBT and vPvB ass	essment No information available
Otherwise adverse effects	The product is insoluble in water. Can be separated out mechanically in purifications plants.

13. DISPOSAL CONSIDERATIONS

Waste treatment methods

Waste material must be disposed of in accordance with the Directive on waste 2008/98/EC as well as other national and local regulations. it is not possible to determine a waste code for this product in accordance with the European Wast Catalogue (EWC) since it is only possible to classify it according to how it is used by the customer. The waste code is to be determined within the EU in liaison with the waste-disposal operator.

Product	Coordinate disposal with the authorities if necessary.
Waste no. (recommended)	101112 101103
Contaminated packaging	Uncontaminated packaging may be taken for recycling
Waste no. (recommended)	150101 150102

14. TRANSPORT INFORMATION

UN number UN proper shipping name	see section 14 in accord	lance with UN shipping name	
Transport by land according to ADR/RID	NO DANGEROUS GOO	DDS	
Inland navigation (ADN)	NO DANGEROUS GOO	DDS	
Marine transport in accordance with IMDG	NO DANGEROUS GOO	DDS	
Air transport in accordance with IMDG	NO DANGEROUS GOO	DDS	
Transport hazard class(es) Packing group Environmental hazards Special precautions for user Transport in bulk according to	see section 14 in accord see section 14 in accord relevant information und		
Commercial 1/1	Certification 1/1	Safety 4/5	Technical Specifications 1/1



INFOSHEET

ATLAS WELDING BLANKET

15. REGULATORY INFORMATION

Safety, health and environme EEC-REGULATIONS:	ntal regulations/legislation specific for the substance or mixture 1967/548 (2008/58, 30. ATP/ 31. ATP); 1991/689 (2001/118); 1999/13; 2004/42;
	648/2004; 1907/2006 (Reach); 1272/2008; 75/324/EWG (2008/47/EG DOT-Classification, ADR (2009); IMDG-Code (34. Amdt.); IATA-DGR (2010).) EH40/2005 Workplace exposure limits with amendments October 2007. CHIP 3/ CHIP 4
Observe employment restrict	
OC (1999/13/CE)	Not applicable Not applicable
00 (1000,10,02)	

16. OTHER INFORMATION

Abbreviations and acronyms:

	-
	ADR = Accord européen relatif au transport international des marchandises Dangereuses par
	Route
	RID = Règlement concernant le transport international ferroviaire de marchandises
	dangereuses
	ADN = Accord européen relatif au transport international des marchandises dangereuses par
	voie de navigation intérieure
	CAS = Chemical Abstracts Service
	CLP = Classification, Labelling and Packaging DMEL = Derived Minimum Effect Level
	DNEL = Derived No Effect Level
	EC50 = Median effective concentration
	ECB = European Chemicals Bureau
	EEC = European Economic Community
	EINECS = European Inventory of Existing Commercial Chemical Substances
	ELINCS = European List of Notified Chemical Substances
	GHS = Globally Harmonized System of Classification and Labelling of Chemicals
	IATA = International Air Transport Association
	IBC-Code = International Code for the Construction and Equipment of Ships carrying
	Dangerous Chemicals in Bulk
	IC50 = Inhibition concentration, 50%
	IMDG = International Maritime Code for Dangerous Goods
	IUCLID = International Uniform ChemicaL Information Database
	LC50 = Lethal concentration, 50%
	LD50 = Median lethal dose
	MARPOL = International Convention for the Prevention of Marine Pollution from Ships
	PBT = Persistent, Bioaccumulative and Toxic substance
	PNEC = Predicted No-Effect Concentration
	REACH = Registration, Evaluation, Authorisation and Restriction of Chemicals
	TLV®/TWA = Threshold limit value – time-weighted average
	TLV®STEL = Threshold limit value – short-time exposure limit
	VOC = Volatile Organic Compounds
	vPvB = very Persistent and very Bioaccumulative
Customs tariff	Not determined

Disclaimer: This information is based on our present knowledge. However, this shall not constitute a guarantee for any specific product features and shall not establish a legally valid contractual relationship.

Safety 5/5



ATLAS WELDING BLANKET

TECHNICAL DATA

Test			Standard*
1. Weave		Atlas 1/7	DIN 61 101 - 1
2. Width		1000 mm	DIN EN 1773
3. Thickness		0,7 mm	DIN EN ISO 2286-3
4. Weight		720 g/m²	DIN 53 854
5. Number of threads	warp	16,0 threads/cm	DIN EN 1049 - 2
	weft	15,0 threads/cm	
6. Yarn count	warp	204 total	DIN EN ISO 2060
	weft	204 total	
7. Filament diameter	warp	9 µm	DIN 53 811
	weft	9 µm	
8. Tensile strength	warp	> 5500 N/5 cm	DIN 53 857 - 1
	weft	> 5000 N/5 cm	

* partly according to the standard

Subject to tolerances

FOSHEE

